

DESCRIPTION: BASALITE MORTAR CEMENT is designed for use in high strength mortars and stuccos. It is a mixture of Portland cement, mortar enhancing admixtures and supplementary materials. BASALITE MORTAR CEMENT is designed to maintain the excellent working properties of masonry cement with added strength and bond.

USES: BASALITE MORTAR CEMENT is formulated for use in Type S mortar and in stucco.

PROJECT	MORTAR CEMENT	LOOSE DAMP SAND	HYDRATED LIME
Type S Mortar	1	2 1/4--3 1/2	1* (see note)
Type N Mortar	2	5 3/4--8 3/4	
Stucco-Scratch Coat	1	2 1/2--4	
Stucco-Brown Coat	1	3--5	
Stucco-Finish Coat	1	1 1/2--3	

*Note: for Type N mortar: By weight – 3 bags of 30kg MORTAR Cement to 1 bag of Lime (22.7kg)

Mixing:

- Blend the dry ingredients together by proportion. Mix only what you can use within 2 hours.
- Add water gradually to the dry ingredients. Mix thoroughly after each addition of water until the product reaches the desired consistency. Mortars and stuccos should be smooth and spreadable. If product drips or runs off the tools, then add more dry ingredients by proportion.
- Use finished product within 2 hours of mixing. If the product starts to set and harden do not add more water to thin it out or re-temper.

LIMITATIONS: BASALITE MORTAR CEMENT must not be used for making concrete. Do not add excess water as it will weaken the final product. A temperature above 5 Celsius must be maintained until product is fully cured.

TECHNICAL DATA: BASALITE MORTAR CEMENT meets CAN CSA 3001-13 “Masonry and Mortar Cement” specifications as well as ASTM C91-12 cement specifications.

PACKAGING: BASALITE MORTAR CEMENT is packaged in 30 kg (66 lb.) triple-lined paper bags.

All Basalite Dry Mix can be custom-packaged to suit specific project requirements.

SAFETY PRECAUTIONS: BASALITE MORTAR CEMENT contains Portland cement. Normal safety wear such as rubber gloves, dust masks and safety glasses, used to handle conventional cement-based products, should be worn. Material Safety Data Sheets are available upon request.

Liability for damages or defective goods shall be limited to the refund of the purchase price or product replacement.