

**DESCRIPTION:** BASALITE STUCCO REPAIR, a pre-blended product conforming to the proportion specifications of ASTM C926. BASALITE STUCCO REPAIR contains a carefully balanced mixture of Portland cement, aggregates, Type 'S' hydrated lime, alkali resistant fibers and stucco enhancing admixtures.

**USES:** BASALITE STUCCO REPAIR is ideal for basecoat stucco applications over woven or welded wire mesh or metal lath. Ideal for repairing stucco.

**ADVANTAGES:** BASALITE STUCCO REPAIR offers the following advantages:

- ⇒ workability
- ⇒ trowellability
- ⇒ adhesion
- ⇒ cohesion
- ⇒ quality controlled
- ⇒ increased productivity

**PROCEDURES:** MIXING: BASALITE STUCCO REPAIR must be mixed with a clean mortar mixer. Use only potable water.

- ⇒ Pour 50ml of water into the mixer for each 5kg (11lbs.) pail of BASALITE STUCCO REPAIR.
- ⇒ Slowly add the contents of 5kg pail into the mixer.
- ⇒ Mix 5 minutes until firm, workable consistency is reached. If more water is needed, slowly add small amounts at a time to bring the stucco up to the desired consistency.
- ⇒ The exact amount of water required will depend upon the quality of the mixer used as well as site conditions. Do not exceed the maximum of 750 ml water per 5 kg (11 lbs) pail.
- ⇒ **WARNING: DO NOT ADD SOAP OR ANY OTHER ADMIXTURE TO BASALITE STUCCO REPAIR**

PLACING: Apply as per the recommendations outlined in ASTM C926, ACI 524R-16 and the Portland Cement Plaster (Stucco) Manual for proper application techniques.

CURING: Stucco must be water cured for 48 hours. Begin fogging or misting with water once the applied stucco has achieved its final set. Hot or windy weather will require additional safeguards, including a minimum of 72hour water curing and/or blockage of direct sunlight and wind.

**RE-TEMPERING:** BASALITE STUCCO REPAIR may be re-tempered once. The re-tempered stucco must be used within 1.5 hours from the start of the initial mixing. All stucco older than 1.5 hours must be discarded.

**COVERAGE:** One 5kg (11lbs) pail of Basalite Stucco Repair will cover approximately 0.234 square meters (2.56 square feet) at 13mm (1/2 inch) thickness.

**LIMITATIONS:** Liability for damages or defective goods shall be limited to the refund of the purchase price or replacement.

**PACKAGING:** BASALITE STUCCO REPAIR is packaged in 5kg (11lbs) pail. All Basalite Dry Mix can be custom-packaged to suit specific project requirements.

**SAFETY PRECAUTIONS:** BASALITE STUCCO REPAIR contains Portland cement and other carefully selected additives. Normal safety wear such as rubber gloves, dust masks and safety glasses used to handle conventional cement-based products should be worn. Safety Data Sheets are available at [www.basalite.ca](http://www.basalite.ca).